

Test Report No. SDHG1308006677FB Date: Aug.15, 2013 Page 1 of 3

HD SUPPLY FACILITIES MAINTENANCE 10641 SCRIPPS SUMMIT CT SAN DIEGO, CA, 92131 U.S.A.

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description : 3.5" VERTICAL BLINDS SGS Ref. No. : GZHG1308028686OT

Manufacturer : DONGGUAN FANCHANG CURTAIN PRODUCTS CO., LTD.

: HD SUPPLY FACILITIES MAINTENANCE Buyer

Country of Destination : U.S.A.

Other Info. : COLOR:WHITE/ALABASTER

Sample Receiving Date : Aug.08, 2013

Test Performing Date : Aug.08, 2013 to Aug.15, 2013

Test Result Summary

No.	Test(s) Requested	Result(s)	Comments				
1	NFPA 701 Test Method 2(flat) 2010 Edition: Standard Methods of Fire Tests for Flame Propagation of Textiles and Films	PASS					
For further details, please refer to the following page(s)							

Signed for and on behalf of SGS-CSTC Co., Ltd.

Irvette Zhang

Approved signatory

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an

1F; Faliding European Industrial Park) lot. 1 Sturtheran Read; Muste Section; Deliang Town Shunde Forthan, Guargiong, Oline 528333 t (86-757) 22805888 f (86-757) 22805888 www.sgsgroup.com.cn 中国·广东·佛山市原德区大良街道办事处五沙顺和南路·号欧洲工业园一号厂房首层 邮编: 528333 t (86-757)22805888 f (86-757)22805858 e sgs.china@sgs.com

ticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com



Test Report

No. SDHG1308006677FB

Date: Aug.15, 2013

Page 2 of 3

Test Conducted:

NFPA 701 Test Method 2(flat) 2010 Edition: Standard Methods of Fire Tests for Flame Propagation of Textiles and Films

Sample Details

Name / Color:	3.5" VERTICAL BLINDS / White
Weight:	1.08 kg/m ²

Test Results:

Original State tested to Chapter 15 of NFPA 701-Method 2 for Flat

Specimen	Char Length (Inches)	After flame (Seconds)	Flaming Residue (Seconds)	Rating
1	6.2	0	0	Pass
2	5.3	0	0	Pass
3	5.8	0	0	Pass
4	6.0	0	0	Pass
5	6.3	0	0	Pass
6	5.5	0	0	Pass
7	4.7	0	0	Pass
8	5.3	0	0	Pass
9	4.5	0	0	Pass
10	5.8	0	0	Pass

Remark:

Requirements:

- 1. The time of individual specimen continues flaming was not more than 2 seconds after the test flame is removed from contact with the specimen.
- 2. The length of char of any single flat specimen does not exceed 435 mm (17.1in).
- 3. The time of portions or residues continues flaming was not more than 2 seconds.

Note:

As per the standard requirement, the sample size were $125 \times 1200 \pm 22$ mm, but the client did not submit suitable size, so as per the client's requirement, the submitted sample overlap and staple.

Conclusion:

The submitted sample met the requirements of NFPA 701 Test Method 2-2010 Edition.

To be continued...

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms-Terms-And-Conditions/Terms-Terms-And-Conditions/Terms-Terms-And-Conditions/Terms-Terms-And-Conditio

ticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

⁽¹⁾ The specimen length parallel to the lengthwise direction of the material.



Test Report

Photo Appendix:

No. SDHG1308006677FB

Date: Aug.15, 2013

Page 3 of 3



End of Report

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-an