

• TRUSTED QUALITY SINCE 1921 •



**HIGH PERFORMANCE
CABINET PAINT**

DESCRIPTION AND USES

Rust-Oleum® High Performance Cabinet paint features fast drying, excellent adhesion and water resistance. These paints are designed to match Seasons Thermofoil doors and drawer fronts.

PRODUCTS

SKU	Description
316196	Natural Oak
316197	Light Maple
316198	Hayward Cherry
316199	Blossom Cherry
316200	Espresso
316201	Moon Shadow (gray)
316503	White

PRODUCT APPLICATION

SURFACE PREPARATION

Surface should be clean of grease and dirt. Apply cabinet deglosser. Scrub with green Scotch-Brite™ pad or similar. Flush with clean water. Wearing gloves, fold a scrub pad in half and apply the deglosser liberally onto the pad. Scrub the entire surface to remove all dirt and contaminants. After deglossing, wipe down the surface with a damp cloth to remove any traces of the cleaner. Finish by wiping down the surface with a clean, lint-free cloth. Rinse thoroughly with fresh water and allow to fully dry.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Before using, stir thoroughly to ensure any settled pigment is re-dispersed. Thinning is not required. Avoid painting in direct sunlight or on hot surfaces. Use a good quality synthetic brush. Avoid excessive brushing as this will reduce film thickness and protection. Use light even strokes to ensure smooth and uniform flow.

DRY & RECOAT TIMES

Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 30 minutes, dry to handle in 1 hour, and fully dry in 2-4 hours.

CLEAN-UP

Clean brush and other application tools immediately with soap and water.

TECHNICAL DATA

HIGH PERFORMANCE CABINET PAINT

PHYSICAL PROPERTIES

		HIGH PERFORMANCE CABINET PAINT
Resin Type		Styrene Acrylic Polymer
Pigment Type		Varies with Color, Limestone
Solvents		Water, Glycol Ethers
Weight	Per Gallon	9.0-10.0 lbs.
	Per Liter	1.07-1.20 kg
Solids	By Weight	34.8-47.5%
	By Volume	26.8-33.5%
Volatile Organic Compounds		<250 g/l (2.08 lbs./gal.)
Recommended Dry Film Thickness (DFT) per Coat		1.0-1.5 mils (25-37.5μ)
Wet Film to Achieve DFT (unthinned material)		3.0-5.5 mils (75-137.5μ)
Practical Coverage at Recommended DFT (assumes 15% material loss)		240-450 sq.ft./gal. (5.9-11.1m ² /l)
Dry Times at 70-80°F (21-27C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hour
	Recoat	2-4 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		>200°F (93°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.